

SeerPak® Renewable Barrier Liner

- Conventionally recyclable, food safe, barrier coated unbleached paper for the manufacture of solid board or corrugate.
- >99.5% Renewable materials
- Exhibits high grease barrier with water resistance.
- FSC or PEFC available

Properties	Method	Unit	Value
Grammage	ISO 536	gsm	107
Thickness	ISO 534	Micron	140
Grease Resistance	T557	Kit	12
Grease Resistance	ISO 16532	Olive Oil	Level 1
Water Resistance Cobb1800	ISO 535	gsm	<40.0
Water Vapour Barrier 23°C/85% RH	ISO 2528	gsm/day	Na
Oxygen Barrier		cm ³ /m ² /day	Na
Heat Seal	Induction	1-5 = low - high energy	NA
Repulpability	CEPI 2	Suitable for Standard Mill recycling. Scale -100% to +100%	+95% Best in class